

Test Report No. <u>9577/17</u> Sassuolo, 12/01/18

Requested by:	FLORIM CERAMICHE S.p.A Via Canaletto 24 – 41042 FIORANO MODENESE (MO)				
For the sample:	Glazed ceramic tiles 30 x 60 x 1,0 cm marked "BRAND CERIM - Serie TIMELESS OF CERIM - Articolo MARFIL GRIP 30x60 cm".			ESS OF CERIM -	
On (date): 20/12/17		Date of receipt in laboratory (sample delivered by the client): 20/12/17			
Test date		From: 20/12/17	То:	20/12/17	

<u>DIN 51097 (11/1992) – Determination of anti – slip properties.</u> <u>Wet-loaded barefoot areas – Walking method – Ramp test</u>

WORKING CONDITIONS:

Size of the tested surface (m):	0,50 x 1,20
Joint width (mm):	2
Grout:	Cement mortar
Surface orientation:	None

RESULTS

Average slip angle:	23,0°
Application range:	A+B

Eng. Giordana Carani Technical approval

Prof. Maria Chiara Bignozzia

The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.